AMENDMENTS TO THE CLAIMS

The claims in this listing will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

- 1. (Currently Amended) Method for producing a fiber-composite material for producing fiber-composite components, comprising combining reinforcement fibers, resin, and a filler, the filler comprising consisting of the reinforcement fibers that have been at least one of ground or cut so that reinforcement fibers and filler in the fiber-composite material consists of the reinforcement fibers and the filler consisting of the reinforcement fibers that have been at least one of ground or cut.
- 2. (Currently Amended) Method according to claim 1, wherein the filler comprises consists of ground fibers having a particle size of less than 2 mm.
- 3. (Currently Amended) Method according to claim 1, wherein the filler comprises consists of cut fibers having a size of less than 20 mm.
- 4. (Previously Presented) Method according to claim 1, wherein the at least one of ground and cut reinforcement fibers is mixed with the resin that forms a subsequent matrix of the fiber-composite component thereby forming a resin filler mixture.
- 5. (Previously Presented) Method according to claim 4, wherein the resin filler mixture is processed into a film.
- 6. (Previously Presented) Method according to claim 5, wherein the resin filler film is applied to a semi-finished textile product.

- 7. (Previously Presented) Method according to claim 6, wherein the resin filler film is introduced into a component mold before the semi-finished textile product is placed in the component mold.
- 8. (Previously Presented) Method according to claim 1, wherein the fiber-composite material is applied into a component mold or onto a semi-finished textile product in a spray method.
- 9. (Previously Presented) Method according to claim 8, wherein the semi-finished textile product sprayed with the resin filler material is also used for producing preforms.
 - 10. (Canceled)
- 11. (Previously Presented) Method according to claim 6, wherein the semi-finished textile product comprises woven fabrics, braided fabrics, knitted fabrics, unidirectional fabrics or multiaxial laid fabrics.
- 12. (Previously Presented) Method according to claim 7, wherein the resin filler film comprises a preform.
- 13. (Currently Amended) The method according to claim 1, wherein the filler comprises consists of ground fibers having a particle size of less than 2 mm, and cut fibers having a size of less than 20 mm.
 - 14. (Withdrawn) Fiber-composite material produced by the method of claim 1.
 - 15. (Withdrawn) Fiber-composite material produced by the method of claim 2.
 - 16. (Withdrawn) Fiber-composite material produced by the method of claim 3.
 - 17. (Withdrawn) Fiber-composite material produced by the method of claim 13.
- 18. (Withdrawn Currently Amended) Fiber-composite material comprising reinforcement fibers, resin, and a filler comprising consisting of the reinforcement fibers that are {P29527 01024603.DOC}

at least one of ground and or cut so that the filler comprises a same material as the reinforcement fibers so that reinforcement fibers and filler in the fiber-composite material consists of the reinforcement fibers and the filler consisting of the reinforcement fibers that have been at least one of ground or cut.

- 19. (Withdrawn Currently Amended) Fiber-composite material according to claim 18, wherein the filler comprises consists of at least one of ground fibers having a particle size of less than 2 mm, and cut fibers having a size of less than 20 mm.
- 20. (Withdrawn Currently Amended) The fiber-composite material according to claim 18, wherein the filler comprises consists of ground fibers having a particle size of less than 2 mm, and cut fibers having a size of less than 20 mm.